



INNOVATIONS FOR LIVING®

CLEAR POINTS INTERNATIONAL CO.,LTD.
224/1 SOI INDHAMARA45 KWANG-DINDAENG
KHET-DINDAENG BANGKOK 10400
TEL: 02-693-9551-3
FAX: 02-693-9554
HOTLINE: 081-912-2823 , 081-131-1188
ID LINE: 0819122823



FOAMULAR® CWI5/CW25

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet



Energy-Saving, Moisture-Resistant XPS Insulation

Cavity Wall Insulation

CWI5: ASTM C578 Type X, 15 psi minimum

CW25: ASTM C578 Type IV, 25 psi minimum

Description

Designed for masonry cavity wall applications, FOAMULAR® extruded polystyrene (XPS) insulation is virtually impervious to moisture. This moisture-resistant property—along with its high R-value, light weight, competitive price and wide range of sizes—makes it ideal for use in a cavity wall system. Pre-cut 16" wide boards yield fast, labor-saving installation.

Key Features

- Excellent long-term stable insulating performance of R-5¹ per inch.
- Exceptional moisture resistance, long-term durability
- Limited lifetime warranty²—maintains 90% of R-value

and covers all ASTM C 578 properties

- The only XPS foam to be GREENGUARD Children & Schools CertifiedSM
- The only XPS foam with certified recycled content—certified by Scientific Certification Systems (SCS) to contain a minimum 20% recycled content
- Will not corrode, rot or support mold growth
- Zero ozone depletion potential with 70% less global warming potential than our previous formula
- Reusable
- Lightweight, durable rigid foam panels are easy to handle and install
- Easy to saw, cut or score
- Not for use in roofing. For roofing applications, use FOAMULAR® THERMAPINK® XPS insulation

Technical Information

This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code. For additional information, consult MSDS or contact Owens Corning World Headquarters at 1-800-GET-PINK®.

All construction should be evaluated for the necessity to provide vapor retarders. See current ASHRAE Handbook of Fundamentals.

FOAMULAR® insulation is a non-structural material and must be installed on framing which is independently braced and structurally adequate to meet required construction and service loading conditions.

FOAMULAR® insulation can be exposed to the exterior during normal construction cycles. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed and still useful insulation.

Standards, Codes Compliance

- Meets ASTM C 578 Type X (CWI5) and Type IV (CW25)
- UL Classified. A copy of UL Classification Certificate U-197





FOAMULAR® CW15/CW25

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

is available at
www.foamular.com

- See ICC-ES ESR-1061 at www.icc-es.org
- ASTM E 119 Fire Resistance Rated Wall Assemblies. See www.foamular.com for details.
- Meets California Quality Standards; HUD UM #71A
- Compliance verification by RADCO (AA-650)

Certifications and Sustainable Features of FOAMULAR® XPS insulation

- FOAMULAR® XPS insulation is reusable
- FOAMULAR® XPS insulation is made with a zero ozone depletion formula
- Certified by Scientific Certification Systems to contain a minimum of 20% pre-consumer recycled polystyrene
- Certified to meet indoor air quality standards under the stringent GREENGUARD Indoor Air Quality Certification ProgramSM, and the GREENGUARD Children & Schools Certification ProgramSM
- Approved under the National Association of Home Builders (NAHB) Research Center Green Seal of Approval
- Utilizing FOAMULAR® XPS insulation can help achieve green building certifications including the U.S. Green Building Council's Leadership in Energy and Environmental Design (LEED®) certification

Typical Physical Properties¹

FOAMULAR® CW15/CW25 Extruded Polystyrene Insulation

Property	Test Method ²	CW15	CW25
Thermal Resistance ³ , R-Value minimum, hr•ft ² •°F/Btu @ 75°F (24°C) mean temperature @ 40°F (4.4°C) mean temperature	ASTM C 518	5.0 5.4	5.0 5.4
Compressive Strength ⁴ , minimum psi	ASTM D 1621	15.0	25.0
Flexural Strength ⁵ , minimum psi	ASTM C 203	40	50
Water Absorption ⁶ , maximum % by volume	ASTM C 272	0.10	0.10
Water Vapor Permeance ⁷ , maximum perm	ASTM E 96	1.10	1.10
Dimensional Stability, maximum % linear change	ASTM D 2126	2.0	2.0
Flame Spread ^{8,9}	ASTM E 84	5	5
Smoke Developed ^{8,9,10}	ASTM E 84	45-175	45-175
Oxygen Index ⁸ , minimum % by volume	ASTM D 2863	24	24

1. Properties shown are representative values for 1" thick material, unless otherwise specified.
2. Modified as required to meet ASTM C 578
3. R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value. Follow the manufacturer's instructions carefully. If a manufacturer's fact sheet is not provided with the material shipment, request this and review it carefully. R-values vary depending on many factors including the mean temperature at which the test is conducted, and the age of the sample at the time of testing. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data. The R-value for FOAMULAR® XPS insulation is provided from testing at two mean temperatures, 40°F and 75°F, and from two aging (conditioning) techniques, 180 day real-time aged (as mandated by ASTM C 578) and a method of accelerated aging sometimes called "Long Term Thermal Resistance" (LTTR) per CAN/ULC 5770-03. The R-value at 180 day real-time age and 75°F mean temperature is commonly used to compare products and is the value printed on the product.
4. Values at yield or 10% deflection, whichever occurs first.
5. Value at yield or 5%, whichever occurs first.
6. Data ranges from 0.00 to value shown due to the level of precision of the test method.
7. Water vapor permeance decreases as thickness increases.
8. These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.
9. Data from Underwriters Laboratories Inc.® classified. See Classification Certificate U-197.
10. ASTM E 84 is thickness-dependent, therefore a range of values is given.

- FOAMULAR® XPS insulation may qualify for The Buy American provision of the American Recovery and Reinvestment Act (ARRA)

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.sustainability.owenscorning.com.

Warranty

FOAMULAR® XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C 578 properties. See actual warranty for complete details, limitations and requirements at www.foamular.com or www.owenscorningcommercial.com.

CLEAR POINTS INTERNATIONAL CO.,LTD.
224/1 SOI INDHAMARA45 KWANG-DINDAENG
KHET-DINDAENG BANGKOK 10400
TEL: 02-693-9551-3
FAX: 02-693-9554
HOTLINE: 081-912-2823 , 081-131-1188
ID LINE: 0819122823

WWW.CLEAR-POINTS.COM
CLEARPOINTS@GMAIL.COM



FOAMULAR® CW15/CW25

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

Product and Packaging Data

FOAMULAR® CW15/CW25 Extruded Polystyrene Insulation

Material				Packaging					Edges
Thickness (in)	Product Dimensions Thickness (in) x Width (in) x Length (in) ¹	Pallet (Unit) Dimensions (typical) Width (ft) x Length (ft) x Height (ft)	Square feet per Pallet	Board feet per Pallet	Bundles per Pallet	Pieces per Bundle	Pieces per Pallet		
CW-15									
1"	1 x 16 x 96	4 x 8 x 8	3,072	3,072	12	24	288	Square	
1-1/2"	1.5 x 16 x 96	4 x 8 x 8	2,048	3,072	12	16	192		
2"	2 x 16 x 96	4 x 8 x 8	1,536	3,072	12	12	144		
2-1/2"	2.5 x 16 x 96	4 x 8 x 8	1,152	2,880	12	9	108		
3"	3 x 16 x 96	4 x 8 x 8	1,024	3,072	12	8	96		
CW-25									
1"	1 x 16 x 96	4 x 8 x 8	3,072	3,072	12	24	288	Square	
1-1/2"	1 1/2 x 16 x 96	4 x 8 x 8	2,048	3,072	12	16	192		
2"	2 x 16 x 96	4 x 8 x 8	1,536	3,072	12	12	144		
2-1/2"	2.5 x 16 x 96	4 x 8 x 8	1,152	2,880	12	9	108		
3"	3 x 16 x 96	4 x 8 x 8	1,024	3,072	12	8	96		

1. Product availability and lead times vary by region and by product. Consult your local Owens Corning sales representative for availability and lead times.

Notes

1. R means the resistance to heat flow; the higher the R-value, the greater the insulating power.
2. See actual warranty for complete details, limitations and requirements.

All products described here may not be available in all geographic markets. Consult your local sales office representative for more information.

For more information on the Owens Corning family of building products, contact your Owens Corning dealer; call 1-800-GET-PINK®, or access our web sites: www.foamular.com and www.owenscorning.com.



CLEAR POINTS INTERNATIONAL CO.,LTD.
 224/1 SOI INDHAMARA45 KWANG-DINDAENG
 KHET-DINDAENG BANGKOK 10400
 TEL: 02-693-9551-3
 FAX: 02-693-9554
 HOTLINE: 081-912-2823 , 081-131-1188
 ID LINE: 0819122823

WWW.CLEAR-POINTS.COM
CLEARPOINTS@GMAIL.COM



FOAMULAR® CWI5/CW25 Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

CLEAR POINTS INTERNATIONAL CO.,LTD.
224/1 SOI INDHAMARA45 KWANG-DINDAENG
KHET-DINDAENG BANGKOK 10400
TEL: 02-693-9551-3
FAX: 02-693-9554
HOTLINE: 081-912-2823 , 081-131-1188
ID LINE: 0819122823

WWW.CLEAR-POINTS.COM
CLEARPOINTS@GMAIL.COM

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.

The GREENGUARD INDOOR AIR QUALITY CERTIFIED mark is registered certification mark used under license through the GREENGUARD Environmental Institute.

This NAHB Research Center Green Approved mark is your assurance that a product is eligible for points toward National Green Building Certification. Visit www.GreenApprovedProducts.com for details.

LEED is a registered trademark of the U.S. Green Building Council.



OWENS CORNING FOAM INSULATION, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1-800-GET-PINK®
www.owenscorning.com

Pub. No. 23156-C. Printed in U.S.A. August 2011. THE PINK PANTHER™ & ©1964-2011 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2011 Owens Corning.

