

COLPHENE 2500

TECHNICAL DATA SHEET APTDS-E-01-01

DESCRIPTION

COLPHENE 2500 is a self-adhesive base sheet membrane composed of SBS modified bitumen. The surface is composed of a cross-laminated HDPE film with superior mechanical properties, the underside is covered with a release protection film.

APPLICATION

- It can be used as both a underlay or reinforcement layer for roof waterproofing systems with standing seam metal roofing panels or bituminous shingle.
- Waterproofing for foundation walls and others below grade vertical surfaces
- Vapour barrier in both conventional and deck roof systems.

INSTALLATION

COLPHENE 2500 must be applied directly onto treated surfaces:

- Brush and dry surface.
- If needed, cover the surface with a coat of primer using a brush or a roller.
- Once dry, put roll into place and set it to the appropriate size.
- Apply primer on the surface.
- Pull on sheet and lay it out while flattening the surface so as to avoid air getting trapped.
- Ideal laying temperature: + 10°C
- Overlap width according to local code.

HEALTH AND ENVIRONMENT

The membrane does not contain any substance that might be detrimental to health or to the environment and complies with generally accepted health standards and Material Safety Data Sheet (MSDS).

QUALITY CONTROL

SOPREMA has always attached the highest importance to quality control. For this reason, we operate an internationally recognized quality system meeting ISO 9001 & ISO 14001 standards, independently monitored and certified.

CLEAR POINT **CLEAR POINTS INTERNATIONAL CO.,LTD.**
224/1 Soi Indhamara45
Kwang Din-Daeng, Khet Din-Daeng,
Bangkok 10400 (THAILAND)
TEL: (662) 693-9551-3 FAX: (662) 693-9554
Line ID : 0819122823
<http://www.clear-points.com>
e-mail : clearpoints@gmail.com



COLPHENE 2500

TECHNICAL DATA SHEET APTDS-E-01-01

PROPERTIES

Composition	COLPHENE 2500
Thickness	1.5mm
Nominal weight	1.5 kg/m ²
Dimension	1 × 20m
Top face	Cross laminated HDPE film
Under face	Silicone-coated removable plastic film

Properties	Test method	COLPHENE 2500	
		Machine Direction (MD)	Cross Machine Direction(CMD)
Tension maximum load (kN/m)	ASTM D5147	4.4	5.7
Elongation at maximum tension (%)	ASTM D5147	400	300
Elongation at break (%)	ASTM D5147	430	310
Elongation at break— bitumen (%)	ASTM D5147	≥1000	
Low temperature flexibility (°C)	ASTM D5147	-20	-20
Water absorption (%)	ASTM D5147	0.4	
Average tear resistance (kN/m)	ASTM D5601	22	38
Static Puncture resistance (N)	ASTM D5601	390	
Lap Adhesion (N/m)	ASTM D1876	1700	
Adhesion to steel plates (N/m)	ASTM D903	1900	
Adhesion to primed concrete (N/m)	ASTM D1000	2100	
Water Vapour Transmission (ng/Pa•s•m2)	ASTM E96 Method B	<2.1	

(All values are nominal)

CLEAR POINT CLEAR POINTS INTERNATIONAL CO.,LTD.
 224/1 Soi Indhamara45,
 Kwang Din-Daeng, Khet Din-Daeng,
 Bangkok 10400 (THAILAND)
 TEL: (662) 693-9551-3 FAX: (662) 693-9554
 Line ID : 0819122823
 http://www.clear-points.com
 e-mail : clearpoints@gmail.com

